



Cite this: *Environ. Sci.: Nano*, 2018, 5, 1078

# Emerging investigator series: the rise of nano-enabled photothermal materials for water evaporation and clean water production by sunlight

Peng Wang  <sup>ab</sup>

Solar driven water evaporation and distillation is an ancient technology, but has been rejuvenated by nano-enabled photothermal materials in the past 4 years. The nano-enabled state-of-the-art photothermal materials are able to harvest a full solar spectrum and convert it to heat with extremely high efficiency. Moreover, photothermal structures with heat loss management have evolved in parallel. These together have led to the steadily and significantly improved energy efficiency of solar evaporation and distillation in the past 4 years. Some unprecedented clean water production rates have been reported in small-scale and fully solar-driven devices. This frontier presents a timely and systematic review of the impressive developments in photothermal nanomaterial discovery, selection, optimization, and photothermal structural designs along with their applications especially in clean water production. The current challenges and future perspectives are provided. This article helps inspire more research efforts from environmental nano communities to push forward practical solar-driven clean water production.

Received 5th February 2018,  
Accepted 19th March 2018

DOI: 10.1039/c8en00156a

rsc.li/es-nano

## Environmental significance

Given the vast abundance and inexhaustibility of sunlight, tapping into solar energy to produce clean water is a viable solution to current global challenges of water scarcity and clean energy shortage. Nano-enabled solar driven water evaporation and distillation have experienced very significant growth in the past 4 years. The CO<sub>2</sub> free clean water production feature of solar evaporation and distillation makes them promising and attractive for small-scale water plants and point-of-use water supply systems. This article highlights recent developments and emerging applications of these solar-driven processes.

## Introduction

Photothermal materials are able to effectively capture light and efficiently convert light energy to heat.<sup>1,2</sup> The generated heat can be utilized for many kinds of applications, such as photothermal therapy,<sup>1</sup> solar electricity generation,<sup>3</sup> clean water production,<sup>4–6</sup> etc. Solar distillation is an ancient technology for solar driven clean water production.<sup>7</sup> In a typical solar distillation apparatus, sunlight is captured and converted to heat by photothermal materials and the heat is used to generate water vapor, which is subsequently condensed to produce fresh water.<sup>8</sup> Solar-driven water evaporation assisted by photothermal materials is an essentially integral part of solar distillation.<sup>9</sup>

The research on utilizing photothermal materials for both solar water evaporation and solar distillation has attracted a fast growing interest in the past 4 years.<sup>4–6</sup> In particular, the zero CO<sub>2</sub> emission feature of solar distillation towards seawater desalination is very contemporarily appealing and relevant in the times of ongoing and ever worsening global warming, clean energy shortage, and water scarcity.<sup>10–13</sup>

<sup>a</sup> Water Desalination and Reuse Center, Division of Biological and Environmental Science and Engineering, King Abdullah University of Science and Technology, Thuwal, 23955-6900 Saudi Arabia. E-mail: peng.wang@kaust.edu.sa

<sup>b</sup> KAUST Solar Center (KSC), King Abdullah University of Science and Technology, Thuwal, 23955-6900 Saudi Arabia



Peng Wang

Professor Peng Wang is currently an associate professor in the Environmental Science and Engineering program at KAUST. He received his Ph.D. degree from the University of California, Santa Barbara (UCSB) in 2008. His research focuses on rational design, synthesis, and application of nanomaterials toward sustainable-energy driven clean water production.



tion of hierarchical graphene foam,<sup>18</sup> cauliflower-shaped hierarchical copper nanostructures,<sup>19</sup> and metal nanoparticle decorated wood<sup>20</sup> exhibited much lower sensitivity to the incident angle of sunlight.

Last but not least, the plasmonic effect of noble metal nanomaterials is wavelength specific and highly dependent on their shapes and sizes.<sup>21</sup> To harvest a wide solar spectrum, metal nanoparticles with a wide size distribution and/or various shapes are combined in some works.<sup>22,23</sup>

## Development of solar photothermal nanomaterials in the past 4 years

The first and foremost important parameter for photothermal materials in solar water evaporation and distillation is their light absorption capability. In comparison, the light-to-heat conversion performance of photothermal materials receives much less attention, not due to the lack of efforts but because most photothermal materials typically possess very high light-to-heat efficiency. In 2017, Wang *et al.* compared the light-to-heat conversion efficiency of MXene and carbon nanotubes (CNTs) and found no discernible difference, with both being close to 100%.<sup>24</sup> This result agreed with the 100% light-to-heat conversion of  $\text{Ti}_2\text{O}_3$  reported by Wu *et al.*<sup>25</sup> and of Au nanoparticles reported by Govorov *et al.*<sup>26</sup>

Various nanomaterials with strong light absorbance in the wide solar spectrum have been intensively investigated in the past 4 years, including carbon based materials, metals, metal oxides, and polymers, among others. Broadly speaking, the light, once absorbed by a photothermal material, induces an electric field which drives mobile carriers inside the crystals of the material, and the energy gained by the carriers turns into heat.<sup>4</sup>


Due to the closely spaced energy levels of the loosely-held  $\pi$  electrons in carbon-based materials, they absorb widely in the entire solar spectrum and the excited electrons relax to their ground state, releasing heat. Carbon-based materials, including carbon black, CNTs, graphene, GO, rGO, *etc.* are among the most well-known photothermal materials because of their broad light absorption, high stability, light weight and low cost. Carbon-based materials contain no toxic metals, possess much better stability under sunlight than polymers, and can be easily made into all kinds of structures with macro-, micro- and nanoscale morphologies desirable for solar thermal applications.<sup>5,18,27–37</sup>

In 2011, Wang *et al.* reported a self-assembled  $\text{Fe}_3\text{O}_4$ /carbon nanocomposite capable of self-floating on top of a water surface for solar water evaporation.<sup>38</sup> In 2014 and 2016, amorphous and low-density hollow carbon spheres with a self-floating property were similarly synthesized from organic polymer precursors for solar water evaporation.<sup>39,40</sup> In 2015, Jiang *et al.* used PDMS as a binder to coat carbon black on a cotton gauze and obtained a superhydrophobic gauze

The solar spectrum at sea level ranges from 280 to 2500 nm.<sup>14</sup> In order to capture solar energy to a great extent, a good photothermal material for solar water evaporation and distillation is expected to absorb widely within the entire solar spectrum. The development of effective photothermal materials has been a very active playground for nanomaterials in the past 4 years. The role of nano as an enabler for the rise of photothermal materials utilizing solar energy can be reflected in the following broad aspects.<sup>4–6,15</sup>

Firstly, almost all of, especially inorganic, photothermal materials have a refractive index greater than 2 (<https://refractiveindex.info/>), leading to their high light reflection ( $>11\%$ ), according to the Fresnel equation.<sup>16</sup> To diminish the reflected light loss, the photothermal materials are typically made into highly porous nanostructures, which results in an extremely low effective refractive index and therefore achieves a much lower light reflection.<sup>17</sup> From a microscopic point of view, the highly porous structures can create multiple reflections inside the pores (Fig. 1) and thus increase light absorption.<sup>16,17</sup>

Secondly, light absorption of a flat surface has a very strong dependence on the incident light angle, while porous nanostructures of the same material show a reduced dependence degree, which is beneficial for solar photothermal materials (Fig. 1).<sup>16</sup> It has been reported that the light absorp-



**Fig. 1** Comparison of (a) a flat surface and (b) a porous structure in terms of their light reflection and dependence on the incident light angle.



semiconductors would ultimately recombine to give rise to heat generation.<sup>77</sup>

In 2016, Huang *et al.* synthesized titania nanocages with a high light trapping capability for solar water evaporation.<sup>78</sup> In 2017,  $\text{TiO}_x$  ( $x < 2$ ) and  $\text{Ti}_2\text{O}_3$  nanoparticles with strong light absorption were reported and their application to solar evaporation and desalination was demonstrated.<sup>25,79</sup> In 2017, oxygen-deficient molybdenum oxide ( $\text{MoO}_3$ ) quantum dots, which possessed a matching-absorption-spectrum to solar light in both visible and near infrared regions, were used for solar water evaporation.<sup>80</sup> In 2017, Ye *et al.* prepared  $\text{Fe}_3\text{O}_4$ ,  $\text{MnFe}_2\text{O}_4$ ,  $\text{ZnFe}_2\text{O}_4$ , and  $\text{CoFe}_2\text{O}_4$  hydrophobic microspheres, which self-assembled into self-floating thin films for solar thermal evaporation.<sup>81</sup> In 2018, Wang *et al.* reported a  $\text{CuCr}_2\text{O}_4$  loaded quartz glass fiber membrane as an extremely thermal stable solar photothermal material which provided potential fouling control for practical solar evaporation and distillation applications.<sup>82</sup>

### Other inorganic nanomaterials

Wang *et al.* investigated the solar driven heating performance of PbS nanoparticles uniformly dispersed in water in 2013.<sup>83</sup> In 2016, Nagao *et al.* reported that the lossy plasmonic resonances of titanium nitride (TiN) nanoparticles were broad enough to cover and effectively absorb the solar spectrum and the TiN nanoparticles, when dispersed in water, showed better performance than Au and carbon black nanoparticles in solar water evaporation.<sup>84</sup> In 2017, Wang *et al.* first reported MXene ( $\text{Ti}_3\text{C}_2$ ) as a full solar spectrum absorber and effective photothermal material for solar water evaporation.<sup>24</sup> Synthesis of hierarchical graphdiyne-based architecture was reported in 2017 for solar thermal evaporation.<sup>85</sup> In 2016, the assembled  $\text{Cu}_7\text{S}_4$  nanocrystal dense film,<sup>86</sup> and in 2017, porous floating copper phosphate combined with PDMS<sup>87</sup> were separately reported as photothermal materials for solar-driven water evaporation.

### Polymers

Polymers provide flexibility and easy moldability that their inorganic counterparts cannot. However, compared with rich inorganic photothermal materials, the choices of stable and water compatible photothermal polymers working within a broad solar spectrum are very limited. In 2015, polypyrrole (PPY), a conjugated conductive polymer, was coated onto a metal mesh using a simple anodization method and the PPY coated mesh showed satisfactory performances in solar water evaporation<sup>88</sup> and desalination.<sup>89</sup> In 2017, polydopamine was introduced as a low-cost and biodegradable photothermal material and has since been used for solar water evaporation and seawater desalination.<sup>90,91</sup> In 2018, Wei and co-workers synthesized a new solar photothermal polymer (poly(1,3,5-hexahydro-1,3,5-triazine)), which could be easily solution processed into a self-floating monolithic and single component foam).<sup>92</sup> The photothermal foams were mechanically

strong, thermally stable to 300 °C and chemically resistant to organic solvents.

Considering their cost, availability, stability, and toxicity,<sup>28</sup> carbon based photothermal materials are largely favorable choices and have been more widely explored in solar evaporation and distillation applications than the others. Some comparative studies have hinted that more expensive Au nanocrystals and MXene had no clearly convincing advantages over relatively inexpensive carbon black and/or CNTs in terms of solar photothermal conversion efficiency.<sup>83</sup> It has to be pointed out that the purpose of this Frontier is to provide a concise overview of the state-of-the-art of this exciting field; more detailed and comprehensive summaries of photothermal materials, including their types, light-to-heat conversion mechanisms, light absorbing characteristics, *etc.* can be found in some recent review articles.<sup>4–6</sup>

## Development of photothermal structures utilizing sunlight

In a conventional bulk heating solar distillation apparatus, bulk water is heated to a high temperature (50–90 °C) for water vapor generation, which results in a slow response to sunlight and a bothersome heat management of using an elaborately installed thermal insulation material over the entire bulk water part.<sup>8,93,94</sup> In the past 4 years, the interfacial heating idea has been widely accepted and utilized in the design of advanced solar distillation apparatuses.<sup>4–6</sup> With an interfacial heating scheme, there is an ultra-fast response to sunlight and the generated heat is mainly confined in the surface water layer, which leaves the bulk water with a much lower temperature and therefore greatly removes the burden of the thermal insulation need of the bulk water body.

Fig. 2 presents the energy balance scheme in a typical interfacial solar water evaporation system, with a photothermal material floating at the air–water interface. In such a system, solar radiation ( $P_{\text{sun}}$ ) is the only energy input which is ultimately split into and is balanced by five energy output pathways: (1) reflective solar radiation ( $P_{\text{rf}}$ ), (2) water



Fig. 2 Energy balance diagram of a solar water evaporation system based on interfacial heating. Note: water evaporation is in open air in this case.





This journal is © The Royal Society of Chemistry 2018

One noteworthy work in the structural design for solar evaporation is that of Chen *et al.* who, in 2016, demonstrated a low-cost and scalable self-floating solar evaporation device capable of generating 100 °C water steam under ambient air conditions without optical concentration.<sup>98</sup> The high temperatures were achieved by using thermal concentration and by carefully reducing  $P_{\text{rf}}$ ,  $P_{\text{cv}}$ ,  $P_{\text{cd}}$ , and  $P_{\text{rd}}$ . The generation of high temperature water vapor under unconcentrated sunlight has the potential to expand the application scope of solar thermal conversion.

## Applications of solar distillation and evaporation

### Solar distillation

There have been considerable efforts to conduct solar distillation using bench-scale simple solar still devices with interfacial heating design. In these devices, a photothermal material with satisfactory sunlight absorption capability floats on the source water surface and a transparent cover (*e.g.*, glass, plastic) serves as the water condensation surface (Fig. 4a). These solar distillation devices are all able to produce potable water with good quality utilizing a variety of source waters, including synthetic seawater,<sup>36,37,48,50,67,92</sup> real seawater,<sup>35,55,99</sup> lab-prepared wastewater,<sup>46,68,97</sup> river water,<sup>49</sup> lake water,<sup>100</sup> and sewage water.<sup>37</sup> Nevertheless, the water production rates of these devices represented only a small improvement relative to the ancient design of a solar still given the dilemma of both transparency and thermal conductivity of the condensation surface in this old-fashioned design.

### Combination of solar-driven interfacial heating with MD

Membrane distillation (MD) is a thermally-driven separation process, in which only vapor molecules transfer through a microporous hydrophobic membrane. The driving force in the MD process is the vapor pressure difference induced by the temperature difference across the hydrophobic membrane.<sup>101</sup> A conventional MD involves heating up the entire

bulk water to a uniform temperature and suffers from interfacial temperature polarization due to the removal of latent heat by water evaporation at the MD membrane.<sup>102</sup> The interfacial temperature polarization decreases the membrane temperature and thus diminishes the net driving force to mass transport water across the MD membrane.<sup>101</sup> The solar-thermal interfacial heating concept has been creatively combined with the MD process to alleviate the aforementioned drawbacks (Fig. 4b). Interfacial heating generates localized heating only on the MD membrane interface and thus eliminates the requirement of heating the entire bulk feed water and at the same time reduces the impact of interfacial temperature polarization.<sup>103–107</sup>

From 2015 to 2017, Fujiwara together with coworkers demonstrated azobenzene dye loaded AAO and PTFE membranes for light driven seawater desalination.<sup>108–110</sup> In 2017, Curcio *et al.* fabricated PVDF MD membranes filled with spherical silver nanoparticles with controlled sizes.<sup>103</sup> Under the illumination of UV light at 366 nm provided by a high pressure UV mercury lamp of 500 W, the membrane surface temperature was 23 K greater than the bulk water, which resulted in an 11 fold increase of the transmembrane water flux, with 0.5 M NaCl being the feed water. In the above designs, the photothermal species/materials were almost uniformly imbedded throughout the pores of the membranes.

In 2017, Li *et al.* reported a carbon black nanoparticle or SiO<sub>2</sub>/Au nanoshell coated MD membrane, which delivered an up to 33% increase in distillate flux when irradiated at 1 sun.<sup>104</sup> Later, Li along with Halas and coworkers fabricated a bi-layered MD membrane structure, consisting of a thin and carbon black nanoparticle impregnated electrospun polyvinyl alcohol (PVA) porous film stacked on a commercial PVDF MD membrane.<sup>12,106</sup> The two designs by Li *et al.*<sup>104,106</sup> had the photothermal materials only on one side of the MD membranes. The nanophotonics-enabled solar membrane distillation (NESMD) system was directly and entirely driven by solar energy. A pilot-scale device with an active area of  $\sim 1 \times 1$  m, when tested outdoor locally at Houston, USA, was able to produce an average clean water flux of 0.5 kg m<sup>-2</sup> h, equivalent




Fig. 4 (a) Simple solar distillation apparatus based on interfacial heating, (b) conceptual design of solar-thermal interfacial heating in MD, and (c) a solar distillation design with a latent heat recovery mechanism.



to ~4 L per day under less than 1 sun ( $700 \text{ W m}^{-2}$ ) illumination for 8 h of sunlight in summer.

In the same year, Chiavazzo and Asinari along with co-workers reported a solar-driven and fully passive distiller, which could be operated in either MD mode or without a membrane.<sup>105</sup> In their design, two major features were noteworthy: multiple cycles of latent-heat recovery and separation of the light-adsorption surface and water evaporation surface (Fig. 4c), both contributing to considerably enhanced energy efficiency. The latent heat from water vapor condensation was collected and recycled back repeatedly to the feed water to drive further water evaporation. The small device, when tested outdoors at Torino, Italy in summer and with real seawater as feed water, produced an unprecedented clean water flux of  $1.77 \text{ kg kW}^{-1} \text{ h}^{-1}$ , equivalent to  $1.24 \text{ kg m}^{-2} \text{ h}$  under  $700 \text{ W m}^{-2}$  solar illumination which exceeds the thermodynamic limit of single-stage solar stills.

### Applications based on solar water evaporation

Some applications based on water removal by solar evaporation have emerged, including salt extraction towards zero liquid discharge desalination, wastewater volume reduction, and salt or heavy metal extraction. In 2017, Mi *et al.* used a GO thin film to evaporate 15 wt% NaCl solution, during which salt crystals accumulated on the GO film surface.<sup>29</sup> The results pointed to the potential application of solar-thermal RO brine treatment toward a zero liquid discharge desalination process.<sup>29</sup> In 2017, Zhu *et al.* used a 3D photothermal structure and extracted Cu and Au salts out of contaminated water by a solar water evaporation process.<sup>97</sup>

### Other emerging applications

There have also been examples of integrating the solar photothermal process along with the energy generation and transformation process, including photocatalysis and electricity generation. In 2016, a bifunctional membrane consisting of a top layer of  $\text{TiO}_2$  nanoparticles, a middle layer of Au nanoparticles, and a bottom layer of AAO was designed for simultaneous photocatalytic degradation of water contaminants and solar-driven evaporation.<sup>68</sup> In 2017, the salt concentration gradient across the water evaporation surface and the bulk water was utilized by Zhou *et al.* who provided the first proof-of-concept of simultaneous solar thermal desalination and electricity generation under natural sunlight illumination.<sup>111</sup> In 2017, a solar thermal collector based on  $\text{SiO}_2/\text{Ag}@\text{TiO}_2$  core-shell nanocomposites was reported by Ho *et al.* for synergistic photothermic driven seawater catalysis to generate hydrogen and to produce desalted water under natural sunlight.<sup>112</sup> In 2018, Ho *et al.* reported simultaneous solar distillation and electricity generation by self-contained monolithic carbon sponges.<sup>113</sup> In 2017, Kim *et al.* used broad light absorbing Au and carbon black and demonstrated their direct solar thermal disinfection effect.<sup>62</sup>

## Challenges and future perspectives

In spite of the amazing achievements made in the past 4 years in photothermal materials, their applications are still at an infant stage and there are significant barriers standing between the *status quo* and large scale and practical applications of solar evaporation and solar distillation. The following are some of the major challenges, which call for much needed research efforts.

### Challenges

(1) There has been no field-accepted guideline on performance evaluation in solar evaporation or distillation research. A review of the literature reveals a large variability in experimental conditions as well as in energy efficiency calculations, which makes it unreliable to directly compare various photothermal materials just by the literature values of their solar energy efficiency and water evaporation rates. (2) The long-term efficacy of many photothermal materials and designs in dealing with realistic waters, such as real seawater, groundwater, river water, and industrial wastewater, has not been confirmed. Dissolved salts, such as NaCl,  $\text{CaSO}_4$ , and  $\text{MgSO}_4$ , in seawater and hypersaline waters, would crystallize during solar evaporation and distillation and their crystallization behaviors are largely unknown in these solar-driven processes. In particular, the influence of salt fouling of the photothermal materials caused by  $\text{Ca}^{2+}$ ,  $\text{Mg}^{2+}$  and other insoluble or sparsely soluble matter has not been investigated. Equally importantly, bio-fouling of the photothermal materials resulting from dissolved organic matter and other bio species present in source waters would be expected, but has been paid little attention. (3) Many impaired source waters contain volatile organic compounds (VOCs), which would evaporate along and be collected together with water during solar distillation. The concentration of the VOCs in the collected distillate may even be enriched by distillation, which is the Achilles' heel of solar distillation and needs to be addressed by more advanced and multifunctional photothermal designs. (4) The intermittent nature of solar light has a profound effect on solar evaporation and distillation systems, but has not been looked at thoroughly enough.

### Future perspectives

From the solar distillation perspective, it does not need any moving parts, electronic devices and high pressure operations, all of which make it attractive and economical especially for small sized water plants, off-grid and point-of-use (POU) potable clean water production apparatus.<sup>114</sup> Moreover, solar distillation produces fresh water from a variety of water sources with impaired water quality and thus is suitable as an emergency response means for natural disaster-impacted, war-torn regions, as well as the sheer volume of impoverished people who lacks access to clean drinking water. Solar evaporation assisted by photothermal materials towards brine or hypersaline water treatment for the purpose





*Environ. Sci.: Nano*, 2018, **5**, 1078–1089 | 1085



- 25 J. Wang, Y. Y. Li, L. Deng, N. N. Wei, Y. K. Weng, S. Dong, D. P. Qi, J. Qiu, X. D. Chen and T. Wu, High-Performance Photothermal Conversion of Narrow-Bandgap  $\text{Ti}_2\text{O}_3$  Nanoparticles, *Adv. Mater.*, 2017, 29(3), 1603730.
- 26 H. H. Richardson, M. T. Carlson, P. J. Tandler, P. Hernandez and A. O. Govorov, Experimental and Theoretical Studies of Light-to-Heat Conversion and Collective Heating Effects in Metal Nanoparticle Solutions, *Nano Lett.*, 2009, 9, 1139–1146.
- 27 X. Zhu, K. Yang and B. Chen, Membranes prepared from graphene-based nanomaterials for sustainable applications: a review, *Environ. Sci.: Nano*, 2017, 4, 2267–2285.
- 28 R. Bjorkland, D. A. Tobias and E. J. Petersen, Increasing evidence indicates low bioaccumulation of carbon nanotubes, *Environ. Sci.: Nano*, 2017, 4, 747–766.
- 29 C. Finnerty, L. Zhang, D. L. Sedlak, K. L. Nelson and B. Mi, Synthetic Graphene Oxide Leaf for Solar Desalination with Zero Liquid Discharge, *Environ. Sci. Technol.*, 2017, 51, 11701–11709.
- 30 Y. Fu, G. Wang, T. Mei, J. Li, J. Wang and X. Wang, Accessible Graphene Aerogel for Efficiently Harvesting Solar Energy, *ACS Sustainable Chem. Eng.*, 2017, 5, 4665–4671.
- 31 X. Hu, W. Xu, L. Zhou, Y. Tan, Y. Wang, S. Zhu and J. Zhu, Tailoring Graphene Oxide-Based Aerogels for Efficient Solar Steam Generation under One Sun, *Adv. Mater.*, 2017, 29, 1604031.
- 32 L. Shi, Y. C. Wang, L. B. Zhang and P. Wang, Rational design of a bi-layered reduced graphene oxide film on polystyrene foam for solar-driven interfacial water evaporation, *J. Mater. Chem. A*, 2017, 5, 16212–16219.
- 33 G. Wang, Y. Fu, X. F. Ma, W. B. Pi, D. W. Liu and X. B. Wang, Reusable reduced graphene oxide based double-layer system modified by polyethylenimine for solar steam generation, *Carbon*, 2017, 114, 117–124.
- 34 J. J. Wang, Z. H. Liu, X. L. Dong, C. E. Hsiung, Y. H. Zhu, L. M. Liu and Y. Han, Microporous cokes formed in zeolite catalysts enable efficient solar evaporation, *J. Mater. Chem. A*, 2017, 5, 6860–6865.
- 35 P. Zhang, J. Li, L. Lv, Y. Zhao and L. Qu, Vertically Aligned Graphene Sheets Membrane for Highly Efficient Solar Thermal Generation of Clean Water, *ACS Nano*, 2017, 11, 5087–5093.
- 36 Y. Wang, C. Wang, X. Song, S. K. Megarajan and H. Jiang, A facile nanocomposite strategy to fabricate a rGO–MWCNT photothermal layer for efficient water evaporation, *J. Mater. Chem. A*, 2018, 6, 963–971.
- 37 Y. Yang, R. Zhao, T. Zhang, K. Zhao, P. Xiao, Y. Ma, P. M. Ajayan, G. Shi and Y. Chen, Graphene-Based Standalone Solar Energy Converter for Water Desalination and Purification, *ACS Nano*, 2018, 12, 829–835.
- 38 Y. Zeng, J. F. Yao, B. A. Horri, K. Wang, Y. Z. Wu, D. Li and H. T. Wang, Solar evaporation enhancement using floating light-absorbing magnetic particles, *Energy Environ. Sci.*, 2011, 4, 4074–4078.
- 39 Y. Zeng, K. Wang, J. F. Yao and H. T. Wang, Hollow carbon beads for significant water evaporation enhancement, *Chem. Eng. Sci.*, 2014, 116, 704–709.
- 40 J. G. Zhou, Z. L. Sun, M. Q. Chen, J. T. Wang, W. M. Qiao, D. H. Long and L. C. Ling, Macroscopic and Mechanically Robust Hollow Carbon Spheres with Superior Oil Adsorption and Light-to-Heat Evaporation Properties, *Adv. Funct. Mater.*, 2016, 26, 5368–5375.
- 41 Y. Liu, J. Chen, D. Guo, M. Cao and L. Jiang, Floatable, Self-Cleaning, and Carbon-Black-Based Superhydrophobic Gauze for the Solar Evaporation Enhancement at the Air–Water Interface, *ACS Appl. Mater. Interfaces*, 2015, 7, 13645–13652.
- 42 Y. Ito, Y. Tanabe, J. Han, T. Fujita, K. Tanigaki and M. Chen, Multifunctional Porous Graphene for High-Efficiency Steam Generation by Heat Localization, *Adv. Mater.*, 2015, 27, 4302–4307.
- 43 S. M. Sajadi, N. Farokhnia, P. Irajizad, M. Hasnain and H. Ghasemi, Flexible artificially-networked structure for ambient/high pressure solar steam generation, *J. Mater. Chem. A*, 2016, 4, 4700–4705.
- 44 G. Wang, Y. Fu, A. K. Guo, T. Mei, J. Y. Wang, J. H. Li and X. B. Wang, Reduced Graphene Oxide–Polyurethane Nanocomposite Foam as a Reusable Photoreceiver for Efficient Solar Steam Generation, *Chem. Mater.*, 2017, 29, 5629–5635.
- 45 H. Ghasemi, G. Ni, A. M. Marconnet, J. Loomis, S. Yerci, N. Miljkovic and G. Chen, Solar steam generation by heat localization, *Nat. Commun.*, 2014, 5, 4449.
- 46 J. Lou, Y. Liu, Z. Wang, D. Zhao, C. Song, J. Wu, N. Dasgupta, W. Zhang, D. Zhang, P. Tao, W. Shang and T. Deng, Bioinspired Multifunctional Paper-Based rGO Composites for Solar-Driven Clean Water Generation, *ACS Appl. Mater. Interfaces*, 2016, 8, 14628–14636.
- 47 Q. Jiang, L. Tian, K. K. Liu, S. Tadepalli, R. Raliya, P. Biswas, R. R. Naik and S. Singamaneni, Bilayered Biofoam for Highly Efficient Solar Steam Generation, *Adv. Mater.*, 2016, 28, 9400–9407.
- 48 X. Li, W. Xu, M. Tang, L. Zhou, B. Zhu, S. Zhu and J. Zhu, Graphene oxide-based efficient and scalable solar desalination under one sun with a confined 2D water path, *Proc. Natl. Acad. Sci. U. S. A.*, 2016, 113, 13953–13958.
- 49 Z. Liu, H. Song, D. Ji, C. Li, A. Cheney, Y. Liu, N. Zhang, X. Zeng, B. Chen, J. Gao, Y. Li, X. Liu, D. Aga, S. Jiang, Z. Yu and Q. Gan, Extremely Cost-Effective and Efficient Solar Vapor Generation under Nonconcentrated Illumination Using Thermally Isolated Black Paper, *Global Chall.*, 2017, 1(2), 1600003.
- 50 Z. Z. Wang, Q. X. Ye, X. B. Liang, J. L. Xu, C. Chang, C. Y. Song, W. Shang, J. B. Wu, P. Tao and T. Deng, Paper-based membranes on silicone floaters for efficient and fast solar-driven interfacial evaporation under one sun, *J. Mater. Chem. A*, 2017, 5, 16359–16368.
- 51 Y. C. Wang, L. B. Zhang and P. Wang, Self-Floating Carbon Nanotube Membrane on Macroporous Silica Substrate for Highly Efficient Solar-Driven Interfacial Water Evaporation, *ACS Sustainable Chem. Eng.*, 2016, 4, 1223–1230.
- 52 C. Chen, Y. Li, J. Song, Z. Yang, Y. Kuang, E. Hitz, C. Jia, A. Gong, F. Jiang, J. Y. Zhu, B. Yang, J. Xie and L. Hu, Highly Flexible and Efficient Solar Steam Generation Device, *Adv. Mater.*, 2017, 29(3), 1701756.



- 53 K. K. Liu, Q. Jiang, S. Tadepallit, R. Raliya, P. Biswas, R. R. Naik and S. Singamaneni, Wood Graphene Oxide Composite for Highly Efficient Solar Steam Generation and Desalination, *ACS Appl. Mater. Interfaces*, 2017, 9, 7675–7681.
- 54 Q. Jiang and S. Singamaneni, Water from Wood: Pouring through Pores, *Joule*, 2017, 1, 429–430.
- 55 M. W. Zhu, Y. J. Li, G. Chen, F. Jiang, Z. Yang, X. G. Luo, Y. B. Wang, S. D. Lacey, J. Q. Dai, C. W. Wang, C. Jia, J. Y. Wan, Y. G. Yao, A. Gong, B. Yang, Z. F. Yu, S. Das and L. B. Hu, Tree-Inspired Design for High-Efficiency Water Extraction, *Adv. Mater.*, 2017, 29(44), 1704107.
- 56 G. B. Xue, K. Liu, Q. Chen, P. H. Yang, J. Li, T. P. Ding, J. J. Duan, B. Qi and J. Zhou, Robust and Low-Cost Flame-Treated Wood for High-Performance Solar Steam Generation, *ACS Appl. Mater. Interfaces*, 2017, 9, 15052–15057.
- 57 H. Liu, C. Chen, G. Chen, Y. Kuang, X. Zhao, J. Song, C. Jia, X. Xu, E. Hitz, H. Xie, S. Wang, F. Jiang, T. Li, Y. Li, A. Gong, R. Yang, S. Das and L. Hu, High-Performance Solar Steam Device with Layered Channels: Artificial Tree with a Reversed Design, *Adv. Energy Mater.*, 2018, 8(8), 1701616.
- 58 C. Jia, Y. Li, Z. Yang, G. Chen, Y. Yao, F. Jiang, Y. Kuang, G. Pastel, H. Xie, B. Yang, S. Das and L. Hu, Rich Mesosstructures Derived from Natural Woods for Solar Steam Generation, *Joule*, 2017, 1, 588–599.
- 59 N. Xu, X. Z. Hu, W. C. Xu, X. Q. Li, L. Zhou, S. N. Zhu and J. Zhu, Mushrooms as Efficient Solar Steam-Generation Devices, *Adv. Mater.*, 2017, 29(28), 1606762.
- 60 Y. Li, T. Gao, Z. Yang, C. Chen, W. Luo, J. Song, E. Hitz, C. Jia, Y. Zhou, B. Liu, B. Yang and L. Hu, 3D-Printed, All-in-One Evaporator for High-Efficiency Solar Steam Generation under 1 Sun Illumination, *Adv. Mater.*, 2017, 29, 1700981.
- 61 P. K. Jain, X. H. Huang, I. H. El-Sayed and M. A. El-Sayed, Noble Metals on the Nanoscale: Optical and Photothermal Properties and Some Applications in Imaging, Sensing, Biology, and Medicine, *Acc. Chem. Res.*, 2008, 41, 1578–1586.
- 62 S. Loeb, C. Li and J.-H. Kim, Solar Photothermal Disinfection using Broadband-Light Absorbing Gold Nanoparticles and Carbon Black, *Environ. Sci. Technol.*, 2018, 52, 205–213.
- 63 O. Neumann, A. S. Urban, J. Day, S. Lal, P. Nordlander and N. J. Halas, Solar Vapor Generation Enabled by Nanoparticles, *ACS Nano*, 2013, 7, 42–49.
- 64 N. J. Hogan, A. S. Urban, C. Ayala-Orozco, A. Pimpinelli, P. Nordlander and N. J. Halas, Nanoparticles Heat through Light Localization, *Nano Lett.*, 2014, 14, 4640–4645.
- 65 Z. Fang, Y.-R. Zhen, O. Neumann, A. Polman, F. J. Garcia de Abajo, P. Nordlander and N. J. Halas, Evolution of Light-Induced Vapor Generation at a Liquid-Immersed Metallic Nanoparticle, *Nano Lett.*, 2013, 13, 1736–1742.
- 66 Z. Wang, Y. Liu, P. Tao, Q. Shen, N. Yi, F. Zhang, Q. Liu, C. Song, D. Zhang, W. Shang and T. Deng, Bio-Inspired Evaporation Through Plasmonic Film of Nanoparticles at the Air–Water Interface, *Small*, 2014, 10, 3234–3239.
- 67 Y. Liu, S. Yu, R. Feng, A. Bernard, Y. Liu, Y. Zhang, H. Duan, W. Shang, P. Tao, C. Song and T. Deng, A Bioinspired, Reusable, Paper-Based System for High-Performance Large-Scale Evaporation, *Adv. Mater.*, 2015, 27, 2768–2774.
- 68 Y. Liu, J. Lou, M. Ni, C. Song, J. Wu, N. P. Dasgupta, P. Tao, W. Shang and T. Deng, Bioinspired Bifunctional Membrane for Efficient Clean Water Generation, *ACS Appl. Mater. Interfaces*, 2016, 8, 772–779.
- 69 S. Yu, Y. Zhang, H. Duan, Y. Liu, X. Quan, P. Tao, W. Shang, J. Wu, C. Song and T. Deng, The impact of surface chemistry on the performance of localized solar-driven evaporation system, *Sci. Rep.*, 2015, 5, 13600.
- 70 K. Bae, G. Kang, S. K. Cho, W. Park, K. Kim and W. J. Padilla, Flexible thin-film black gold membranes with ultrabroadband plasmonic nanofocusing for efficient solar vapour generation, *Nat. Commun.*, 2015, 6, 10103.
- 71 L. Tian, J. Luan, K.-K. Liu, Q. Jiang, S. Tadepalli, M. K. Gupta, R. R. Naik and S. Singamaneni, Plasmonic Biofoam: A Versatile Optically Active Material, *Nano Lett.*, 2016, 16, 609–616.
- 72 L. Zhou, S. Zhuang, C. He, Y. Tan, Z. Wang and J. Zhu, Self-assembled spectrum selective plasmonic absorbers with tunable bandwidth for solar energy conversion, *Nano Energy*, 2017, 32, 195–200.
- 73 C. Liu, J. Huang, C.-E. Hsiung, Y. Tian, J. Wang, Y. Han and A. Fratalocchi, High-Performance Large-Scale Solar Steam Generation with Nanolayers of Reusable Biomimetic Nanoparticles, *Advanced Sustainable Systems*, 2017, 1, 1600013.
- 74 W. Sun, G. Zhong, C. Kübel, A. A. Jelle, C. Qian, L. Wang, M. Ebrahimi, L. M. Reyes, A. S. Helmy and G. A. Ozin, Size-Tunable Photothermal Germanium Nanocrystals, *Angew. Chem., Int. Ed.*, 2017, 56, 6329–6334.
- 75 M. Chen, Y. He, J. Huang and J. Zhu, Synthesis and solar photo-thermal conversion of Au, Ag, and Au-Ag blended plasmonic nanoparticles, *Energy Convers. Manage.*, 2016, 127, 293–300.
- 76 M. S. Zielinski, J.-W. Choi, T. La Grange, M. Modestino, S. M. H. Hashemi, Y. Pu, S. Birkhold, J. A. Hubbell and D. Psaltis, Hollow Mesoporous Plasmonic Nanoshells for Enhanced Solar Vapor Generation, *Nano Lett.*, 2016, 16, 2159–2167.
- 77 M. Umlauff, J. Hoffmann, H. Kalt, W. Langbein, J. M. Hvam, M. Scholl, J. Söllner, M. Heuken, B. Jobst and D. Hommel, Direct observation of free-exciton thermalization in quantum-well structures, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 1998, 57, 1390–1393.
- 78 G. Zhu, J. Xu, W. Zhao and F. Huang, Constructing Black Titania with Unique Nanocage Structure for Solar Desalination, *ACS Appl. Mater. Interfaces*, 2016, 8, 31716–31721.
- 79 M. Ye, J. Jia, Z. Wu, C. Qian, R. Chen, P. G. O'Brien, W. Sun, Y. Dong and G. A. Ozin, Synthesis of Black TiO<sub>x</sub> Nanoparticles by Mg Reduction of TiO<sub>2</sub> Nanocrystals and their Application for Solar Water Evaporation, *Adv. Energy Mater.*, 2017, 7, 1601811.



- This article is licensed under a Creative Commons Attribution 3.0 Unported Licence.





- Azobenzene Modified Anodized Alumina Membranes, *ACS Nano*, 2015, **9**, 5705–5712.
- 109 M. Fujiwara and M. Kikuchi, Solar desalination of seawater using double-dye-modified PTFE membrane, *Water Res.*, 2017, **127**, 96–103.
  - 110 M. Fujiwara, Water desalination using visible light by disperse red 1 modified PTFE membrane, *Desalination*, 2017, **404**, 79–86.
  - 111 P. H. Yang, K. Liu, Q. Chen, J. Li, J. J. Duan, G. B. Xue, Z. S. Xu, W. K. Xie and J. Zhou, Solar-driven simultaneous steam production and electricity generation from salinity, *Energy Environ. Sci.*, 2017, **10**, 1923–1927.
  - 112 M. Gao, P. K. N. Connor and G. W. Ho, Plasmonic photothermal directed broadband sunlight harnessing for seawater catalysis and desalination, *Energy Environ. Sci.*, 2016, **9**, 3151–3160.
  - 113 L. Zhu, M. Gao, C. K. N. Peh, X. Wang and G. W. Ho, Self-Contained Monolithic Carbon Sponges for Solar-Driven Interfacial Water Evaporation Distillation and Electricity Generation, *Adv. Energy Mater.*, 2018, 1702149, DOI: 10.1002/aenm.201702149.
  - 114 C. N. Li, Y. Goswami and E. Stefanakos, Solar assisted sea water desalination: A review, *Renewable Sustainable Energy Rev.*, 2013, **19**, 136–163.

